

Attorney Docket No.: 5762.200-US
Application Serial No.: 09/577,694
Filed: May 22, 2000
Inventors: Sorensen et al.
Via Facsimile: 571-273-8300

IN THE CLAIMS

Claims (1-62) – Cancelled

63. (Previously Presented) A stopper comprising an injection-mouldable material, comprising: a blend of a butyl based rubber and a polyolefin, wherein the butyl based rubber is present in an amount of 70-90 % by weight and the polyolefin is present in an amount of 30-10 % by weight, and wherein the combination of the butyl based rubber and the polyolefin results in a reduced leakage of substances compared to the leakage of substances from a stopper made from a butyl based rubber alone and wherein the injection-mouldable material, further comprises: 10 % by weight or less of fillers and 1% by weight or less of additives, provided that the injection-mouldable material comprises other than a thermoplastic elastomer.

64. (Previously Presented) The stopper according to claim 63 having a hardness of 40-80 Shore

65. (Previously Presented) The stopper according to the claim 63 having a hardness of 45-75 Shore A.

66. (Previously Presented).The stopper according claim 63 having a hardness of 65-75 Shore A.

67. (Previously Presented) The stopper according to claim 63 for a medical container, comprising a blend of 13-25 % by weight of a polyolefin and 75-87 % by weight of a butyl based rubber.

68. (Previously Presented) The stopper according to claim 63, wherein the polyolefin is selected from the group of polyolefines consisting of polypropylene and polyethylene.

Attorney Docket No.: 5762.200-US
Application Serial No.: 09/577,694
Filed: May 22, 2000
Inventors: Sorensen et al.
Via Facsimile: 571-273-8300

69. (Previously Presented New) The stopper claim 63, wherein the butyl based rubber is halogenated butyl.
70. (Previously Presented) The stopper claim 63, wherein the butyl based rubber is a bromobutyl.
71. (Previously Presented) The stopper according to claim 63, wherein the butyl based rubber is at least partially cross-linked.
72. (Previously Presented) The stopper according to claim 63 wherein the stopper has a substantially circular cross-section.
73. (Previously Presented) A medical container for storing a liquid medicament, comprising a distal and a proximal end portion and at least one wall defining an interior space for such liquid medicament, wherein one of the end portions comprises a stopper comprising: an injection-mouldable material, comprising: a blend of butyl based rubber and a polyolefin, wherein the butyl based rubber is present in an amount of 70-90 % by weight and the polyolefin is present in an amount of 30-10 % by weight, and wherein the combination of the butyl based rubber and the polyolefin results in a reduced leakage of substances compared to the leakage of substances from a stopper made from a butyl based rubber alone and wherein the injection-mouldable material, further comprises: 10 % by weight or less of fillers and 1% by weight or less of additives, provided that the injection-mouldable material comprises other than a thermoplastic elastomer.

Attorney Docket No.: 5762.200-US
Application Serial No.: 09/577,694
Filed: May 22, 2000
Inventors: Sorensen et al.
Via Facsimile: 571-273-8300

74. (Previously Presented) The medical container according to claim 72, wherein the at least one wall is non-flexible.

75. (Cancelled)

76. (Cancelled).

77. (Previously Presented) A stopper comprising an injection-mouldable material, consisting essentially of: a blend of a butyl based rubber and a polyolefin, wherein the butyl based rubber is present in an amount of 70-90 % by weight and wherein additives are optionally present in an amount not exceeding 1% by weight and fillers are optionally present in an amount less than 10% by weight and wherein the balance of the material is polyolefin, and wherein the combination of the butyl based rubber and the polyolefin results in a reduced leakage of substances compared to the leakage of substances from a stopper made from a butyl based rubber alone.

78. (Previously Presented) The stopper according to claim 77 having a hardness of 40-80 Shore A.

79. (Previously Presented) The stopper according to the claim 77 having a hardness of 65-75 Shore A.

80. (Previously Presented) The stopper according to claim 77 for a medical container, wherein the injection-mouldable material, consists essentially of: a blend of 13-25 % by weight of a polyolefin and 75-87 % by weight of a butyl based rubber.

Attorney Docket No.: 5762.200-US
Application Serial No.: 09/577,694
Filed: May 22, 2000
Inventors: Sorensen et al.
Via Facsimile: 571-273-8300

81. (Previously Presented) The stopper according to claim 77, wherein the polyolefin is selected from the group of polyolefines consisting of polypropylene and polyethylene.

82. (Previously Presented) The stopper claim 77, wherein the butyl based rubber is halogenated butyl.

83. (Previously Presented) The stopper claim 77, wherein the butyl based rubber is a bromobutyl.

84. (Previously Presented) The stopper according to claim 77, wherein the butyl based rubber is at least partially cross-linked.

85. (Previously Presented) The stopper according to claim 77 wherein the stopper has a substantially circular cross-section.